

A 3M Company

Dyneon™

Fluoroelastomer

FE 5522X

Features and Benefits

- Composition: Low fluorine content terpolymer of vinylidene fluoride, hexafluoropropylene, and tetrafluoroethylene
- Low viscosity gum stock without incorporated curatives
- Process targets: Injection and transfer molding
- Amine or bisphenol curable
- Improved low temperature flexibility over standard dipolymers and terpolymers

Typical Properties (Data not for specification purposes)

Fluorine Content [QMC 50.18.3.C]	65.5%
Specific Gravity [QMC 14.10.C]	1.80
Color	Translucent, Off-White
Solubility	Ketones and Esters
Mooney Viscosity ML 1 + 10 @ 121°C (250°F) [3M 2.14.4.C]	Approx. 29

Recommended Processing Procedures

Dyneon™ FE 5522X can be compounded using standard water cooled internal mixers or two-roll mills with standard fillers and ingredients utilized in typical fluoroelastomer formulations. The “dry” ingredients should be blended before adding to the masticated gum. For best results, FE 5522X should be banded on the mill several minutes prior to adding the blended dry ingredients. Once mixed, the compounded stocks have good scorch resistance and storage stability.


Product Form

FE 5522X is packaged in slab form and individual 27.5 lb. (12.5 kg) green polyethylene bags in 55.1 lb. (25.0 kg) boxes.

Safety/Toxicology

Follow recommended handling precautions for use of Dyneon fluoroelastomers. General handling precautions include: (1) Store and use all Dyneon fluoroelastomers only in well ventilated areas. (2) Do not smoke in areas contaminated with dust from Dyneon fluoroelastomers. (3) Avoid eye contact. (4) After handling Dyneon fluoroelastomers wash any contacted skin with soap and water.

Potential hazards, including evolution of toxic vapors, do exist during compounding or processing under high temperature conditions. Before processing Dyneon fluoroelastomers, consult the product MSDS (Material Safety Data Sheet) and follow all label directions and handling precautions. You should also read and follow all directions from other compound ingredient suppliers. Material Safety Data Sheets on Dyneon products are available from your Dyneon Sales Representative or by dialing 651-733-5353.



ISO 9001/QS-9000

All Dyneon™ fluoroelastomers are manufactured at ISO 9001 registered facilities. Dyneon fluoroelastomers produced in North America are manufactured at QS-9000 registered facilities.

Typical Properties of Vulcanizate (Data not for specification purposes)

Compound	phr
FE 5522X	100
MT Black (N990)	30
MgO	3
Ca(OH) ₂	6
Phosphonium accelerator	1.0
Dihydroxy crosslinker	2.0

Typical Rheological Properties Monsanto Moving Die Rheometer (MDR2000®) 100 cpm, 0.5° Arc, 6 minutes [QCM 2.19.1.C]

Temperature °C (°F)	177°	(350°)
ML, Minimum Torque, inch-lb (dN m)	0.9	(1.0)
ts2, Time to 2 inch-lb rise from minimum - minutes	1.3	
t'50, Time to 50% cure - minutes	1.5	
t'90, Time to 90% cure - minutes	2.1	
MH, Maximum Torque, inch-lb (dN m)	22.0	(24.9)

Typical Physical Properties [QCM 125.3.C and 125.17.C] Press Cure 5 minutes @ 177°C (350°F) Post Cure 24 hours @ 260°C (500°F)

Tensile, psi (Mpa)	2000	(13.8)
100% Modulus, psi (Mpa)	950	(6.5)
Elongation at break, %	175	
Hardness, Shore A (ASTM D 2240)	75	

Compression Set, %, [ASTM D 395 Method B (O-rings)]

Aged 70 hours @ 200°C (392°F)	20
-------------------------------	----

TR10 [ASTM D 1329] °C (°F) -19 (-2)

Technical Information and Test Data

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients. No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

Product Identification

The "X" product designation indicates that this is a newly commercialized product and Dyneon reserves the right to make additional process modifications without notice to purchasers as long as the product meets Dyneon published specifications. Once the commercial production process for this product is standardized, the "X" designation will be dropped from the product code.

A 3M Company

Important Notice:

Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it.

The following is made in lieu of all express and implied warranties (including warranties of merchantability and fitness for a particular purpose): If a Dyneon product is proved to be defective, Dyneon's only obligation, and user's only remedy, will be, at Dyneon's option, to replace the quantity of product shown to be defective when user received it or to refund user's purchase price. In no event will Dyneon be liable for any direct, indirect, special, incidental, or consequential loss or damage, regardless of legal theory, such as breach of warranty or contract, negligence, or strict liability.

© Dyneon 2001

Issued: 05/01

Printed in USA
98-0504-1360-2
All Rights Reserved

Dyneon LLC
6744 33rd Street North
Oakdale, MN 55128
Phone: +1 800 723 9127
+1 651 733 5353
Fax: +1 651 737 7686

www.dyneon.com

Dyneon is a trademark of Dyneon
MDR2000 is a trademark of Monsanto